



Il colore italiano dal 1831

# LONG OPEN-TIME GLAZE

TECHNICAL DATA SHEET  
COD. 7AD024





## DECORATIVE GLAZE

- Clear decorative product with veiled effect, based on acrylic polymers in a water dispersion. High open time improves applicability and facilitates use, helping avoid the formation of unsightly seams.

## TYPICAL PHYSICAL AND CHEMICAL CHARACTERISTICS

APPEARANCE	Matt
COMPOSITION	Special acrylic binders and matting agents
BROOKFIELD VISCOSITY	1,350 ± 150 cP G3 V20 at 70°F
C.O.V. / V.O.C	Max. 350 g/L (2.92 lbs/gal).
COLOR	Neutral. Can be tinted using tinting systems

## TYPICAL APPLICATION CHARACTERISTICS

	EFFECTIVE COVERAGE	650-800 sq ft / U.S. gal depending on the substrate and technique
	DRYING (at 70°F and 65% H.R.)	Touch dry: 4-6 hours* Fully dry: 24 hours
	DILUTION	Ready to use
	TOOLS	Roller, brush, sponge, glove, etc.

## APPLICATION SYSTEM

**SUBSTRATES:** Civil plaster, plasterwork, plasterboard, skim-coated walls, wood, etc., suitably prepared.

**SUBSTRATE PREPARATION:** Substrates must be sound, dry, clean, firm and free of damp patches and traces of dirt, grease, mold, etc. Remove flaking or chalky old paintwork by brushing or sanding. Serious imperfections, deficiencies, cracks and peeling must be removed and filled with Boero Water-Resistant Gypsum Powder.

**In the case of chalky paint and surfaces, prepare the substrate with suitable fixative primer.**

Stir the product carefully.

\*In conditions of high humidity, the above times may increase.



Il colore italiano dal 1831

# LONG OPEN-TIME GLAZE

COD. 7AD024

## **RECOMMENDED APPLICATION TECHNIQUE** (See website for How-To Videos [www.boerousa.com](http://www.boerousa.com))

Apply the product to the decorated surface (e.g. washable water-based paint) using the desired tool and technique.

## **GENERAL INFORMATION AND NOTICES**

Clean tools immediately after use with water.

Keep the product in a cool place and do not allow to freeze. Do not apply at temperatures below 40°F.

*The technical information provided above is the result of careful laboratory testing and practical experience. Nevertheless, as the product is often used outside our control, we are unable to guarantee the quality of the end result. This information is subject to review by the Company. Please carefully read the "GENERAL RECOMMENDATIONS".*

CQ Rev. 1 - October 2018



**Boero USA, Inc.**  
1209 Orange Street  
Wilmington, DE 19801  
800 935-6596  
[www.boerousa.com](http://www.boerousa.com)

MADE IN ITALY