



Il colore italiano dal 1831

METALLIC PAINT

TECHNICAL DATA SHEET

COD. 7AD023


DECORATIVE FINISH FOR INTERIORS WITH A DELICATE METALLIC EFFECT

- Decorative satin-finish product with a delicate metallic effect. Resistance to scratching and washing and low dirt pick-up.
- Applicable by roller, brush and spray, this product is ideal for decorating interior surfaces, in settings including private homes, showrooms, stores, offices, public establishments and others.
- For greater resistance to scratching and surface stress, re-coat with a transparent protective finish (e.g. Clearcoat).

TYPICAL CHEMICAL AND PHYSICAL CHARACTERISTICS

APPEARANCE	Smooth metallic satin-finish
COMPOSITION	Special urethane binders and high quality pigments
BROOKFIELD VISCOSITY	3,500 ± 500 cP G4 V20 at 70°F
C.O.V. / V.O.C	Max. 250 g/L (2.09 lbs/gal).
COLOR	Aluminum, Gold, Pearl, Neutral Can be tinted using tinting systems

TYPICAL APPLICATION CHARACTERISTICS

	EFFECTIVE COVERAGE	320-400 sq ft / U.S. gal depending on the substrate and thickness applied
	DRYING (at 70°F and 65% H.R.)	Touch dry: 1-2 hours Fully dry: 18-24 hours
	DILUTION	Trowel: ready to use - Brush, roller: 5 - 10% Spray: 20% water
	TOOLS	Roller, brush, Boero stainless-steel flex trowel, spray

APPLICATION SYSTEM

SUBSTRATES: Civil plaster, plasterwork, plasterboard, skim-coated walls, wood, etc., suitably prepared.

SUBSTRATE PREPARATION: Substrates must be sound, dry, clean, firm and free of damp patches and traces of dirt, grease, mold, etc. Remove flaking or chalky old paintwork by brushing or sanding. Serious imperfections, deficiencies, cracks and peeling must be removed and filled with Boero Water-Resistant Gypsum Powder.

In the case of chalky paint and surfaces, prepare the substrate with suitable fixative primer.



Il colore italiano dal 1831

METALLIC PAINT

COD. 7AD023

APPLICATION OF BASECOAT

Apply 2 coats of an eg-shel paint in a similar color to the *Boero Metallic Paint* color.

APPLICATION OF METALLIC PAINT (See website for How-To Videos www.boerousa.com)

The *Boero Metallic Paint* creates a fine metallic finish and can be applied using a microfiber roller, brush, trowel or spray equipment.

Random Rolled Pattern: Dilute 5%-10% with water. Using a microfiber, mini roller in corners and edges and a 9" microfiber roller in the large areas, apply the *Boero Metallic Paint* in random rolled directions (up, down and diagonally, creating random "curving X's"). You may roll the *Boero Metallic Paint* in a normal vertical manner and then immediately "Back-Roll" using microfiber mini roller to create the random pattern. Avoid allowing the *Boero Metallic Paint* to dry with vertical lines as this may create unwanted "striping".

Brush: Dilute 5%-10% with water. You may apply the *Boero Metallic Paint* directly to the surface using a brush in a random "X" pattern or random roll as listed above and then immediately "Back-Brush" to create your desired pattern.

Sprayed Effect: Dilute 20% and spray with airless or HVLP spray equipment in multiple thin coats.

Troweled Effect: Do not dilute. Apply with a *Boero Stainless-Steel Flex Trowel*.

GENERAL INFORMATION AND NOTICES

Clean tools immediately after use with water.

Keep the product in a cool place and do not allow to freeze. Do not apply at temperatures below 40°F.

The technical information provided above is the result of careful laboratory testing and practical experience. Nevertheless, as the product is often used outside our control, we are unable to guarantee the quality of the end result. This information is subject to review by the Company.

Please carefully read the "GENERAL RECOMMENDATIONS".

CQ Rev. 2 - October 2018



Boero USA, Inc.
1209 Orange Street
Wilmington, DE 19801
800 935-6596
www.boerousa.com

MADE IN ITALY